





AEROFOAM XPE



CROSSED LINKED CLOSED CELL POLYOLEFIN FOAM THERMAL INSULATION

FEATURES

AEROFOAM-XPE is a flexible thermal insulation made of closed cell cross linked polyolefin foam reinforced by heat laminated Aluminium foil



Almost Zero Water Vapour Permeability and Water Absorption

Condensation is the major problem caused by an insufficient insulation. AEROFOAM-XPE having more than 90% closed cell material in addition to the aluminium foil face can be classified as vapour barrier as per ASHRAE and British Standards recommendation even without additional vapour barrier coatings or foil.

Passed a Wide Range of Fire and Smoke Tests

AEROFOAM-XPE had been tested and passed a variety of international standards for building materials. In cases of fire, people staying at higher levels of a structure would not be harmed by the fire but by the smoke density and toxicity. AEROFOAM-XPE passed the concentration limits of combustion gases as per ISO 5659 - 2 IMO resolution MSC 61 (67) 1996 ANNEX 1, PART 2.



Safe, Fast & Easy Installation

Being an integrated insulation material with closed cell polyolefin foam and aluminium foil face and further supplied with a specially developed acrylic adhesive, AEROFOAM-XPE does not require any additional materials like vapour barrier coatings thus cuts the installation time up to a third. AEROFOAM-XPE is a closed cell material and does not emit any loose fibres that can cause irritations to both installers and occupants.

Environment Friendly

AEROFOAM-XPE is CFC and HCFC free and does not contain nor use in its production any of the substances that contribute to Ozone depletion potential nor those listed as Non-Ozone depletion substances with global warming potential.




TECHNICAL COMPARISON

AGAINST COMMONLY USED INSULATION MATERIALS AEROFOAM-XPE FOAM vs FIBERGLASS vs ELASTOMERIC RUBBER

PROPERTY	AEROFOAM-XPE	FIBERGLASS	ELASTOMERIC RUBBER
MATERIAL CONSTRUCTION	Closed cell cross linked polyolefin foam composite, heat laminated to aluminium foil face.	Resin bonded glass fibers	Extruded PVC-Nitrile rubber
STRUCTURE	Fine cells with completely closed cell structure. No loose fibers	Fibrous material, completely open cell, loose fibers	Closed cell material
INSTALLATION REQUIREMENTS	Integrated material. No additional materials required No special protective coverings required	Requires vapour barrier coatings and adhesives	UV Coatings required for outdoor installations
THERMAL CONDUCTIVITY, k ASTM C518	0.034 W/mK @ 23°C	0.035-0.037 W/mK @ 24°C	0.036-0.038 W/mK @ 24°C
DENSITY, ASTM D1622	30 ± 3 kg/m ³	24 kg/m ³	25-35 kg/m ³
WATER VAPOR PERMEABILITY, ASTM E96	0.000 perm-in	75 perm-in (FG only)	0.2 perm-in
SMOKE DENSITY AND TOXICITY ISO 5659-2 with gas analysis to IMO MSC 61(67)	Smoke Density: Dm<200 Smoke Toxicity: Satisfies maximum allowable concentrations for the ff combustion gases: CO, HCl, HBr, HF, HCN, Nox, SO	Not Available	Halogenated/chlorinated byproducts are produced upon combustion
ENVIRONMENTAL CONCERNS CFC & HCFC Chlorinated Compounds ODP & GWP	CFC & HCFC Free; no chlorinated compounds; does not contribute to Ozone Depletion Potential and Global Warming Potential	CFC & HCFC Free	CFC & HCFC Free; presence of chlorinated and halogenated compounds

Information given above is given in good faith and to the best of our knowledge. Data are taken from common publications like brochures/catalogues, etc. However, due to large number of manufacturers, some data may slightly vary. It is recommended that the data are verified by the interested parties before any decisions as to their suitability are made.

PRODUCT STRUCTURE



AEROFOAM-XPE is a closed cell cross linked polyolefin foam mainly used as thermal insulation of air conditioning air ducts, water pipelines, as well as under slab and tank insulation.

AEROFOAM-XPE Insulation is reinforced with heat bonded pure aluminium foil and factory applied specially developed adhesive liner enabling fast and simple installation.

PRODUCT SIZES

AEROFOAM-XPE SHEETS

Thickness	Size of Roll/Sheet (length x width)
13 mm	20m x 1.2m
20 mm	20m x 1.2m
25 mm	2.4m x 1.2m
30 mm	2.4m x 1.2m

AEROFOAM-XPE TUBES

Thickness: 13mm, 20mm and 30mm
ID Range: 22mm (1/2") to 165mm (6")

Note: Other sizes are available on request



OTHER MATERIALS AVAILABLE

AEROFOAM SPECIALITY TAPES	Standard Sizes & Packaging		
	Width (mm)	Length (yards)	Rolls/Box
Special Aluminium Tape	48	30	24
	72	30	16
	96	30	12

TESTING STANDARDS

TEST PROCEDURE	TEST NAME	TESTED BY	PLACE OF TEST	TEST RESULTS
BS476 Part 7	Surface spread of flame	BW	UK	Class 1
BS 6853:1999	Determination of Weighted Summation of Toxic Fume, R	BW	UK	R=0.77
ISO 5659(2) IMO Resolution MSC61(67) 1996:Annex 1, Part 2	Smoke & Toxicity Test	BW	UK	Ds<200 (Gas toxicity analysis below)

BW - Bodycote Warrington (Exova)

GAS		Limit (ppm)	Reading (ppm)		
			Condition 1	Condition 2	Condition 3
Carbon Monoxide	CO	1450	9	8	23
Hydrochloric Acid	HCL	600	ND	ND	ND
Hydrogen Bromide	HBr	600	ND	ND	ND
Hydrogen Fluoride	HF	600	ND	ND	ND
Hydrogen Cyanide	HCN	140	ND	ND	3
Nitrous Fumes	NO _x	350	29	ND	ND
Sulphur Dioxide	SO ₂	120	ND	ND	ND

ND - Not Detected

Condition 1 : 25kW/m² in the presence of a pilot flame

Condition 2 : 25kW/m² in the absence of a pilot flame

Condition 3 : 50kW/m² in the absence of a pilot flame

EXTENSIVE DISTRIBUTION NETWORK WITH OFFICES ACROSS THE GCC AND INDIA



INSTALLATION INSTRUCTIONS

I. Duct Insulation

A. Wrap Around Installation (usually used for 15mm thickness and below)

1. Cut AEROFOAM-XPE insulation to the required length. Always allow 10-15mm excess for final adjustment. Lay the duct on the floor. It is advisable to use a soft sheet, board or any other suitable covering to the floor to avoid damage on the insulation.

2. Peel off a small section of the adhesive paper. Start off with around 100mm. Align the insulation edge with duct edge and gently lower the sheet exposing only required adhesive and padding firmly the insulation as it lay on the duct from the fixed edge moving to the other edge ensuring air is expelled.

3. Once one side is fixed, turn the duct to expose bare side. Repeat until completely covered avoiding pulling of the insulation on edges to ensure the insulation thickness on the corners will be maintained the same.

4. On the final side, ensure the insulation length reaches the same level as the starting edge. Trim off excess length with a sharp knife until it is leveled with adjacent side. Use AEROFOAM aluminium foil tape to seal the joints (2" on butted joints and 3" on corner joints).

***The same procedure is to be followed on a round duct ensuring the edges are butted firmly and seal with AEROFOAM aluminium foil tape.

B. Cut Section Installation (usually used for 20mm thickness and above)

1. Cut four sections of AEROFOAM-XPE insulation ensuring edges to be of the same level as adjacent sides.

2. Use AEROFOAM aluminium foil tape to seal the joints (2" on butted joints and 3" on corner joints).

C. Special Shape Installation



AEROFOAM-XPE polyolefin foam insulation is a very flexible material and can easily be shaped around any particular duct part like elbows, reducers and T-sections. Just cut AEROFOAM-XPE according to shape and size and remove the adhesive paper and press to the shaped surface. Use AEROFOAM aluminium foil tape to seal the joints.

II. Pipe Insulation

1. AEROFOAM-XPE pipe insulation for pipe sizes 1/2" (21mm ID) to 6" (165mm ID) are pre-formed to give a snug fit on pipes and comes with a longitudinal slit for ease of installation. For larger sizes, follow the same procedures as in round ducts.

2. Open the slit of the insulation and insert the pipe. Apply standard glue or sealant on the edges.

3. After ensuring the glue has been cured properly, cover the joints using AEROFOAM aluminium foil tapes.



TECHINICAL DATA

Technical Specification	Test Standard	AEROFOAM-XPE
Material Characteristics		Crossed-linked closed cell polyolefin foam reinforced with heat laminated embossed pure aluminium foil
Sheets / Rolls		Comes with factory applied adhesive backing
Pipe Sections		Pre-formed to give a snug-fit on pipes and supplied with a longitudinal slit
Structure		Completely closed cell. No loose fibres
Malleability		Excellent flexibility and high resilience to deformation
Color		Grayish Black (other colors available depending on volume)
Density		30 kg/m ³ (foam only)
Thermal Conductivity	ASTM C518	0.034 W/mK @ 24°C
Water Vapour Permeability	ASTM E96	0.00 g/h.m ²
Water Vapour Permeance	ASTM E96	0.00 perms
Water Absorption (Vol. %) 28 days	BSEN 12087: 1997 Method 2A	0.3
Surface spread of flame	BS 476 Part 7	Class 1
Toxic Fume, R	BS6853:1999	0.77
Smoke & Toxicity	ISO 5659-2 IMO MSC 61 (67)1996	Ds<200, passed toxicity level
Operating Temperature		-80 °C to 100 °C
Environmental Concerns		CFC & HCFC Free Non contributing to ODP & GWP
Ozone Resistance		Excellent
UV Resistance		Excellent. No additional UV coatings required

Distributed by:

 **Ramesh Hira**

Head Office: P.O. Box 50673, Dubai - UAE, Tel : +971 4 8848414, Fax : +971 4 8848434

E-mail: enquiry@rhira.com, Website: www.rhira.com, www.aerofoam.ae



U.A.E
Dubai (Showroom)
Tel: +971 4 2288988
Fax: +971 4 2233983
Abu Dhabi
Tel: +971 2 6347815
Fax: +971 2 6347825

Oman
P.O.Box. 167,
P.C 102,
Ghoubra,
Sultanate of Oman
Tel: +968 24495919
Fax: +968 244 96649

**Doha
Qatar**
Tel: +974 4467 4779
Fax: +974 4467 3514

Kuwait
P.O.Box 867,
Zipcode 15259,
Souk Dakhill, Kuwait
Cell: +965 99691822
+965 99691823

Saudi Arabia
Al Khobar
Tel: +966 3 8811784
Fax: +966 3 8811748
Riyadh:
+966 50 71 69 180
+966 56 52 62 970
Jeddah:
+966 54 26 96 455

India
Seven Star Trade Links Pvt. Ltd
Andheri (E),
Mumbai - 400 059
Tel: +91 22 4015 2555
Fax: +91 22 4015 2444